FINAL REPORT

CERTIFICATE No.: 28563

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Berrima Daily Despatch Shrinkage Limited Cement
PRODUCED AT: Boral Cement Limited Berrima
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: BDDSL2603240
DATE DESPATCHED: 11/08/2026

PROPERTY	REQUIREMENTS OF AS 3972			RESULT	
Compressive Strength (AS/NZS 2350.11)					
3 Day				37.5	MPa
7 Day	Minimum	35	MPa	48.6	MPa
28 Day	Minimum	45	MPa	61.3	MPa
Setting Time (AS/NZS 2350.4)					
Initial	Minimum	45	mins	120	mins
Final	Maximum	600	mins	165	mins
Soundness (AS/NZS 2350.5)	Maximum	5	mm	0	mm
SO_3 (AS 2350.2)*	Maximum	3.5	%	2.6	%
Cl (AS 2350.2)*	Maximum	0.10	%	0.04	%
Shrinkage (AS 2350.13)					
28 Day Mean	Maximum	750	μstrain	590	μstrain

OTHER REPORTABLE PROPERTIES

CHEMICAL

K_2O	(AS 2350.2)*	0.55	%
Na_2O	(AS 2350.2)*	0.07	%
LOI	(AS 2350.2)*	4.3	%

PHYSICAL

Normal Consistency	(AS/NZS 2350.3)	28.0	%
Fineness Index	(AS/NZS 2350.8)	405	m^2/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.
This cement is a Type SL (GP) cement with up to 7.5% limestone mineral addition.
*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst

Accredited for compliance with ISO/IEC 17025 - Testing