

# FINAL REPORT

CERTIFICATE No.: 27797



Boral Cement Limited  
ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222

**TEST CERTIFICATE OF:** Berrima Daily Despatch High Early Strength Cement  
**PRODUCED AT:** Boral Cement Limited Berrima  
**TESTED AT:** Boral Cement QA Laboratory  
**SAMPLE IDENTIFICATION:** BWDHE2504716  
**DATE DESPATCHED:** 10/12/2025

PROPERTY	REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS/NZS 2350.11)				
3 Day	Minimum	25 MPa		41.2 MPa
7 Day	Minimum	40 MPa		53.2 MPa
28 Day				64.6 MPa
Setting Time (AS/NZS 2350.4)				
Initial	Minimum	45 mins		90 mins
Final	Maximum	360 mins		120 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm		1 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %		2.9 %
Cl (AS 2350.2)	Maximum	0.10 %		0.02 %

## OTHER REPORTABLE PROPERTIES

CHEMICAL	PHYSICAL		
K <sub>2</sub> O (AS 2350.2) 0.55 %	Normal Consistency (AS/NZS 2350.3)	29.5 %	
Na <sub>2</sub> O (AS 2350.2) 0.07 %	Fineness Index (AS/NZS 2350.8)	455 m <sup>2</sup> /kg	
LOI (AS 2350.2) 1.2 %			

## REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type HE (GP) cement.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1



Melody Mancenido  
(Technical Services Manager)

Date of Issue: 1/15/2026