FINAL REPORT

CERTIFICATE No.: 28595

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Berrima Daily Despatch High Early Strength Cement
PRODUCED AT: Boral Cement Limited Berrima
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: BWDHE2603361
DATE DESPATCHED: 18/08/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day	Minimum	25 MPa	42.4 MPa
7 Day	Minimum	40 MPa	52.7 MPa
28 Day			64.8 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	120 mins
Final	Maximum	360 mins	135 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	0 mm
SO_3 (AS 2350.2)*	Maximum	3.5 %	2.9 %
Cl (AS 2350.2)*	Maximum	0.10 %	0.03 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K_2O	(AS 2350.2)*	0.52 %
Na_2O	(AS 2350.2)*	0.08 %
LOI	(AS 2350.2)*	1.4 %

PHYSICAL

Normal Consistency	(AS/NZS 2350.3)	29.8 %
Fineness Index	(AS/NZS 2350.8)	475 m^2/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.
This cement is a Type HE (GP) cement.
*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst

Accredited for compliance with ISO/IEC 17025 - Testing