

FINAL REPORT

CERTIFICATE No.: 26864



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch General Purpose Bulk Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: GDDGP2500410
DATE DESPATCHED: 9/02/2025

| PROPERTY | REQUIREMENTS OF AS 3972 | | RESULT |
|-----------------------------------|-------------------------|----------|----------|
| Compressive Strength (AS 2350.11) | | | |
| 3 Day | Minimum | 25 MPa | 37.9 MPa |
| 7 Day | Minimum | 40 MPa | 50.7 MPa |
| 28 Day | | | 64.7 MPa |
| Setting Time (AS 2350.4) | | | |
| Initial | Minimum | 45 mins | 105 mins |
| Final | Maximum | 360 mins | 150 mins |
| Soundness (AS 2350.5) | Maximum | 5 mm | 0 mm |
| SO ₃ (AS 2350.2) | Maximum | 3.5 % | 2.9 % |
| Cl (AS 2350.2) | Maximum | 0.10 % | 0.01 % |

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.36 %
Na₂O (AS 2350.2) 0.33 %
LOI (AS 2350.2) 2.5 %

PHYSICAL

Normal Consistency (AS 2350.3) 28.0 %
Fineness Index (AS 2350.8) 375 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Melody Mancenido
(Technical Services Manager)

Date of Issue: 17/04/2025