FINAL REPORT

CERTIFICATE No.: 27549



Boral Cement Limited ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch General Purpose Bulk Cement

PRODUCED AT: Boral Cement Limited Geelong

TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: GDDGP2503467

DATE DESPATCHED: 16/09/2025

PROPERTY		REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS 2350.11)				
3 Day	·				36.9 MPa
7 Day		Minimum	35 MPa		49.6 MPa
28 Day		Minimum	45 MPa		64.6 MPa
Setting Time (AS 2350.	4)				
Initial		Minimum	45 mins		120 mins
Final		Maximum	360 mins		165 mins
Soundness (AS 2350.5)		Maximum	5 mm		1 mm
SO ₃ (AS 2350.2)		Maximum	3.5 %		2.9 %
CI (AS 2350.2)		Maximum	0.10 %		0.02 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K ₂ O (AS 2350.2)	0.39 %		Normal Consistency	y (AS 2350.3)	27.8 %
Na ₂ O (AS 2350.2)	0.26 %		Fineness Index	(AS 2350.8)	$390 \text{ m}^2/\text{kg}$
LOI (AS 2350.2)	3.0 %			•	`

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.

Melody Mancenido
(Technical Services Manager)

Date of Issue: 24/10/2025

Accredited for compliance with ISO/IEC 17025 - Testing
NATA Accreditation Number: 530 / 531 Page 1 of 1