

FINAL REPORT

CERTIFICATE No.: 28438



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch General Purpose Bulk Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: GDDGP2602709
DATE DESPATCHED: 30/06/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			41.6 MPa
7 Day	Minimum	35 MPa	52.6 MPa
28 Day	Minimum	45 MPa	65.8 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	105 mins
Final	Maximum	360 mins	135 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)*	Maximum	3.5 %	2.9 %
Cl (AS 2350.2)*	Maximum	0.10 %	0.03 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2)* 0.39 %
Na₂O (AS 2350.2)* 0.29 %
LOI (AS 2350.2)* 3.0 %

PHYSICAL

Normal Consistency (AS 2350.3) 28.2 %
Fineness Index (AS 2350.8) 410 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.

*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1

Date of Issue: 12/08/2026