

FINAL REPORT

CERTIFICATE No.: 28126



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong High Early Strength Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: GWDHE2601236
DATE DESPATCHED: 25/03/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	42.9 MPa
7 Day	Minimum	40 MPa	55.9 MPa
28 Day			66.6 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	90 mins
Final	Maximum	360 mins	105 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)*	Maximum	3.5 %	3.0 %
Cl (AS 2350.2)*	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2)* 0.33 %
Na₂O (AS 2350.2)* 0.29 %
LOI (AS 2350.2)* 1.0 %

PHYSICAL

Normal Consistency (AS 2350.3) 31.8 %
Fineness Index (AS 2350.8) 495 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type HE (GP) cement with up to 7.5% mineral addition.

*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1

Date of Issue: 6/15/2026