

FINAL REPORT

CERTIFICATE No.: 28374



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong High Early Strength Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: GWDHE2602332
DATE DESPATCHED: 9/06/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	40.6 MPa
7 Day	Minimum	40 MPa	52.6 MPa
28 Day			63.4 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	90 mins
Final	Maximum	360 mins	120 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)*	Maximum	3.5 %	2.9 %
Cl (AS 2350.2)*	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2)* 0.36 %
Na₂O (AS 2350.2)* 0.27 %
LOI (AS 2350.2)* 0.9 %

PHYSICAL

Normal Consistency (AS 2350.3) 31.5 %
Fineness Index (AS 2350.8) 460 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type HE (GP) cement with up to 7.5% mineral addition.

*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1

Date of Issue: 12/08/2026