FINAL REPORT

CERTIFICATE No.: 28612

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong High Early Strength Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: GWDHE2603431
DATE DESPATCHED: 17/08/2026

PROPERTY	REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS 2350.11)				
3 Day	Minimum	25	MPa	43.4 MPa
7 Day	Minimum	40	MPa	53.0 MPa
28 Day				66.4 MPa
Setting Time (AS 2350.4)				
Initial	Minimum	45	mins	90 mins
Final	Maximum	360	mins	105 mins
Soundness (AS 2350.5)	Maximum	5	mm	1 mm
SO_3 (AS 2350.2)*	Maximum	3.5	%	3.0 %
Cl (AS 2350.2)*	Maximum	0.10	%	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K_2O	(AS 2350.2)*	0.31	%
Na_2O	(AS 2350.2)*	0.27	%
LOI	(AS 2350.2)*	0.8	%

PHYSICAL

Normal Consistency	(AS 2350.3)	31.7	%
Fineness Index	(AS 2350.8)	470	m^2/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type HE (GP) cement with up to 7.5% mineral addition.

*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst

Accredited for compliance with ISO/IEC 17025 - Testing