

# FINAL REPORT

CERTIFICATE No.: 24989



Boral Cement Limited  
N 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222

**TEST CERTIFICATE OF:** Marulan Quicklime Fines - Despatch Composite  
**PRODUCED AT:** Boral Cement Limited Marulan  
**TESTED AT:** Berrima Works Laboratory  
**SAMPLE IDENTIFICATION:** LDQLF2302270  
**DATE SAMPLED:** for date ending 10/06/2023

PROPERTY	RESULT
Chemical Composition (AS 4489.5.1)	
CaO	90.7 %
MgO	0.8 %
Al <sub>2</sub> O <sub>3</sub>	0.6 %
SiO <sub>2</sub>	1.4 %
K <sub>2</sub> O	0.1 %
Fe <sub>2</sub> O <sub>3</sub>	0.3 %
LOI (AS 4489.7.1)	5.6 %
ALI as CaO (AS 4489.6.1)	83.9 %
Slaking (AS 4489.3.1)	
Temperature Rise at 30 s	30.0 °C
Temperature Rise at 3 min	42.5 °C
Total Temperature Rise	44.0 °C
Total Active Slaking Time	4.3 mins
Residue on Slaking	0.58 %
Particle Size Distribution * (AS 1141.11.1)	
< 4.75 mm	100 %
< 2.36 mm	100 %
< 1.18 mm	99 %
< 600 µm	94 %

## REMARKS

Sampling not carried out by laboratory. Samples tested as received.

\* Samples are not washed.



Accredited for compliance with ISO/IEC 17025 - Testing

A handwritten signature in blue ink, appearing to read "Marc Smith".

Marc Smith  
Technical Services Manager