

# FINAL REPORT

CERTIFICATE No.: 27849



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

**TEST CERTIFICATE OF:** Marulan Quicklime Fines - Despatch Composite  
**PRODUCED AT:** Boral Cement Limited Marulan  
**TESTED AT:** Boral Cement QA Laboratory  
**SAMPLE IDENTIFICATION:** LDQLF2504924  
**DATE SAMPLED:** for date ending 17/12/2025

| PROPERTY                                    | RESULT   |
|---|----------|
| Chemical Composition (AS 4489.5.1)          |          |
| CaO   | 93.9 %   |
| MgO   | 0.5 %    |
| Al <sub>2</sub> O <sub>3</sub>              | 0.1 %    |
| SiO <sub>2</sub>                            | 0.4 %    |
| K <sub>2</sub> O                            | 0.0 %    |
| Fe <sub>2</sub> O <sub>3</sub>              | 0.1 %    |
| LOI (AS 4489.7.1)                           | 4.2 %    |
| ALI as CaO (AS 4489.6.1)                    | 87.9 %   |
| Slaking (AS 4489.3.1)                       |          |
| Temperature Rise at 30 s                    | 47.5 °C  |
| Temperature Rise at 3 min                   | 53.5 °C  |
| Total Temperature Rise                      | 53.5 °C  |
| Total Active Slaking Time                   | 3.0 mins |
| Residue on Slaking                          | 0.42 %   |
| Particle Size Distribution * (AS 1141.11.1) |          |
| < 4.75 mm                                   | 100 %    |
| < 2.36 mm                                   | 100 %    |
| < 1.18 mm                                   | 99 %     |
| < 600 µm                                    | 95 %     |

## REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

\* Samples are not washed.



Accredited for compliance with ISO/IEC 17025 - Testing

Melody Mancenido  
(Technical Services Manager)