FINAL REPORT

CERTIFICATE No.: 28627

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Marulan Quicklime Fines - Despatch Composite
PRODUCED AT: Boral Cement Limited Marulan
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: LDQLF2603465
DATE SAMPLED: for date ending 19/08/2026

PROPERTY	RESULT
Chemical Composition (AS 4489.5.1)	
CaO	90.6 %
MgO	0.7 %
Al_2O_3	0.5 %
SiO_2	1.2 %
K_2O	0.1 %
Fe_2O_3	0.2 %
LOI (AS 4489.7.1)	5.9 %
ALI as CaO (AS 4489.6.1)	86.4 %
Slaking (AS 4489.3.1)	
Temperature Rise at 30 s	40.0 ºC
Temperature Rise at 3 min	49.0 ºC
Total Temperature Rise	51.0 ºC
Total Active Slaking Time	7.0 mins
Residue on Slaking	0.48 %
Particle Size Distribution * (AS 1141.11.1)	
< 4.75 mm	100 %
< 2.36 mm	100 %
< 1.18 mm	99 %
< 600 µm	89 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

* Samples are not washed.

Accredited for compliance with ISO/IEC 17025 - Testing

Taleb Hallal
Chemical Analyst