

FINAL REPORT

CERTIFICATE No.: 26115



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bagged Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MBGGP2402548
DATE DESPATCHED: 6/12/2024

| PROPERTY | REQUIREMENTS OF AS 3972 | | RESULT |
|---------------------------------------|-------------------------|----------|----------|
| Compressive Strength (AS/NZS 2350.11) | | | |
| 3 Day | | | 33.6 MPa |
| 7 Day | Minimum | 35 MPa | 46.1 MPa |
| 28 Day | Minimum | 45 MPa | 60.4 MPa |
| Setting Time (AS/NZS 2350.4) | | | |
| Initial | Minimum | 45 mins | 150 mins |
| Final | Maximum | 360 mins | 195 mins |
| Soundness (AS/NZS 2350.5) | Maximum | 5 mm | 0 mm |
| SO ₃ (AS 2350.2) | Maximum | 3.5 % | 2.6 % |
| CI (AS 2350.2) | Maximum | 0.10 % | 0.02 % |

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.63 %
Na₂O (AS 2350.2) 0.07 %
LOI (AS 2350.2) 2.4 %

PHYSICAL

Normal Consistency (AS/NZS 2350.3) 27.3 %
Fineness Index (AS/NZS 2350.8) 375 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Jason Nairn
National Technical Manager
Date of Issue: 7/26/2024