

## FINAL REPORT

CERTIFICATE No.: 27665



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

**TEST CERTIFICATE OF:** Maldon Daily Despatch General Purpose Bagged Cement  
**PRODUCED AT:** Boral Cement Limited Maldon  
**TESTED AT:** Boral Cement QA Laboratory  
**SAMPLE IDENTIFICATION:** MBGGP2504014  
**DATE DESPATCHED:** 27/10/2025

PROPERTY	REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS/NZS 2350.11)				
3 Day				29.0 MPa
7 Day	Minimum	35 MPa		40.7 MPa
28 Day	Minimum	45 MPa		56.0 MPa
Setting Time (AS/NZS 2350.4)				
Initial	Minimum	45 mins		150 mins
Final	Maximum	360 mins		180 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm		1 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %		2.7 %
Cl (AS 2350.2)	Maximum	0.10 %		0.02 %

### OTHER REPORTABLE PROPERTIES

CHEMICAL	PHYSICAL		
K <sub>2</sub> O (AS 2350.2)	0.55 %	Normal Consistency (AS/NZS 2350.3)	26.3 %
Na <sub>2</sub> O (AS 2350.2)	0.06 %	Fineness Index (AS/NZS 2350.8)	365 m <sup>2</sup> /kg
LOI (AS 2350.2)	4.1 %		

### REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1



Melody Mancenido  
Technical Services Manager

Date of Issue: 12/19/2025