

FINAL REPORT

CERTIFICATE No.: 26898



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Bagged Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MBGOW2500495
DATE DESPATCHED: 19/02/2025

| PROPERTY | REQUIREMENTS OF AS 3972 | | RESULT |
|---------------------------------------|-------------------------|----------|----------|
| Compressive Strength (AS/NZS 2350.11) | | | |
| 3 Day | | | 37.4 MPa |
| 7 Day | Minimum | 35 MPa | 47.2 MPa |
| 28 Day | Minimum | 45 MPa | 60.6 MPa |
| Setting Time (AS/NZS 2350.4) | | | |
| Initial | Minimum | 45 mins | 105 mins |
| Final | Maximum | 360 mins | 0 mins |
| Soundness (AS/NZS 2350.5) | Maximum | 5 mm | 0 mm |
| SO ₃ (AS 2350.2) | Maximum | 3.5 % | 2.7 % |
| CI (AS 2350.2) | Maximum | 0.10 % | 0.01 % |

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.39 %
Na₂O (AS 2350.2) 0.10 %
LOI (AS 2350.2) 4.4 %

PHYSICAL

Normal Consistency (AS/NZS 2350.3) 28.0 %
Fineness Index (AS/NZS 2350.8) 350 m²/kg
Brightness * (TM 10.01.12) 70.2 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

Melody Mancenido
(Technical Services Manager)