

FINAL REPORT

CERTIFICATE No.: 27910



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Bagged Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: MBGOW2600207
DATE DESPATCHED: 27/01/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			41.1 MPa
7 Day	Minimum	35 MPa	50.9 MPa
28 Day	Minimum	45 MPa	63.9 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	120 mins
Final	Maximum	360 mins	150 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)*	Maximum	3.5 %	2.8 %
CI (AS 2350.2)*	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2)* 0.36 %
Na₂O (AS 2350.2)* 0.08 %
LOI (AS 2350.2)* 4.1 %

PHYSICAL

Normal Consistency (AS/NZS 2350.3) 28.3 %
Fineness Index (AS/NZS 2350.8) 380 m²/kg
Brightness ** (TM 10.01.12) 71.5 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GP cement with up to 7.5% mineral addition.

*The authorised signatory for AS2530.2 is Taleb Hallal

** NATA accreditation does not cover the performance of this service.

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst



Accredited for compliance with ISO/IEC 17025 - Testing