FINAL REPORT

CERTIFICATE No.: 25827



Boral Cement Limited ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

TESTED AT: Berrima Works Lal
SAMPLE IDENTIFICATION: MDDBU2401004

DATE DESPATCHED: 3/12/2024

PROPERTY	REQUIREM	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)				
3 Day				18.8 MPa
7 Day	Minimum	20 MPa		29.2 MPa
28 Day	Minimum	35 MPa		47.1 MPa
Setting Time (AS/NZS 2350.4)				
Initial	Minimum	45 mins		180 mins
Final	Maximum	600 mins		255 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm		0 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %		2.1 %
CI (AS 2350.2)	Maximum	0.10 %		0.01 %
OTHER REPORTABLE PROPERTIES				
CHEMICAL		PHYSICAL		
		Normal Consistency	(AS/NZS 2350.3)	27.5 %
		Fineness Index	(AS/NZS 2350.8)	330 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Accredited for compliance with ISO/IEC 17025 - Testing

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GB cement with nominally 35% slag.

Jul

Marc Smith
Technical Services Manager

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 6/29/2024