## **FINAL REPORT**

**CERTIFICATE No.:** 26841



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement

PRODUCED AT: Boral Cement Limited Maldon

**TESTED AT:** Berrima Works Laboratory

**SAMPLE IDENTIFICATION:** MDDBU2500271 **DATE DESPATCHED:** 4/02/2025

PROPERTY	REQUIREM	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)				
3 Day				20.1 MPa
7 Day	Minimum	20 MPa		31.7 MPa
28 Day	Minimum	35 MPa		52.6 MPa
Setting Time (AS/NZS 2350.4)				
Initial	Minimum	45 mins		165 mins
Final	Maximum	600 mins		210 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm		0 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %		2.5 %
CI (AS 2350.2)	Maximum	0.10 %		0.01 %
OTHER REPORTABLE PROPERTIES				
CHEMICAL		PHYSICAL		
		Normal Consistency	(AS/NZS 2350.3)	28.2 %
		Fineness Index	(AS/NZS 2350.8)	335 m <sup>2</sup> /kg

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GB cement with nominally 35% slag.

Band

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531 Page 1 of 1

Melody Mancenido (Technical Services Manager)

Date of Issue: 30/05/2025