

FINAL REPORT

CERTIFICATE No.: 27340



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement Laboratory
SAMPLE IDENTIFICATION: MDDBU2502474
DATE DESPATCHED: 14/07/2025

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			20.9 MPa
7 Day	Minimum	20 MPa	34.2 MPa
28 Day	Minimum	35 MPa	54.3 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	150 mins
Final	Maximum	600 mins	210 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.7 %
Cl (AS 2350.2)	Maximum	0.10 %	0.04 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency (AS/NZS 2350.3) 28.8 %
Fineness Index (AS/NZS 2350.8) 350 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GB cement with nominally 35% slag.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 2

Melody Mancenido
(Technical Services Manager)

Date of Issue: 12/19/2025

