

FINAL REPORT

CERTIFICATE No.: 28433



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement Laboratory
SAMPLE IDENTIFICATION: MDDBU2602680
DATE DESPATCHED: 6/07/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			19.0 MPa
7 Day	Minimum	20 MPa	29.4 MPa
28 Day	Minimum	35 MPa	48.2 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	180 mins
Final	Maximum	600 mins	225 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)*	Maximum	3.5 %	2.8 %
CI (AS 2350.2)*	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency	(AS/NZS 2350.3)	28.5 %
Fineness Index	(AS/NZS 2350.8)	350 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type GB cement with nominally 35% slag.

*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst



Accredited for compliance with ISO/IEC 17025 - Testing