FINAL REPORT

CERTIFICATE No.: 28635

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement Laboratory
SAMPLE IDENTIFICATION: MDDBU2603407
DATE DESPATCHED: 22/08/2026

PROPERTY	REQUIREMENTS OF AS 3972			RESULT	
Compressive Strength (AS/NZS 2350.11)					
3 Day				18.5	MPa
7 Day	Minimum	20	MPa	29.2	MPa
28 Day	Minimum	35	MPa	51.3	MPa
Setting Time (AS/NZS 2350.4)					
Initial	Minimum	45	mins	165	mins
Final	Maximum	600	mins	210	mins
Soundness (AS/NZS 2350.5)	Maximum	5	mm	1	mm
SO_3 (AS 2350.2)*	Maximum	3.5	%	2.7	%
Cl (AS 2350.2)*	Maximum	0.10	%	0.01	%

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency	(AS/NZS 2350.3)	27.8	%
Fineness Index	(AS/NZS 2350.8)	350	m^2/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.
This cement is a Type GB cement with nominally 35% slag.
*The authorised signatory for AS2530.2 is Taleb Hallal

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst

Accredited for compliance with ISO/IEC 17025 - Testing