

FINAL REPORT

CERTIFICATE No.: 25712



Boral Cement Limited

ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Environment
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDNM2400343
DATE DESPATCHED: 5/02/2024

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.2 %
LOI (AS 3583.3)		-0.7 %
SO ₃ (AS 2350.2; TM 10.01.07)		0.1 %
MgO (AS 2350.2)	≤ 15.0 %	5.6 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	12.9 %
Fe ₂ O ₃ (AS 2350.2)		0.9 %
expressed as FeO *		0.8 %
Mn ₂ O ₃ (AS 2350.2)		0.5 %
expressed as MnO *		0.4 %
Total Alkali (AS 2350.2)		0.5 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
Fineness passing 45µm sieve (AS/NZS 3583.1)		99 %
Fineness Index (AS/NZS 2350.8)		440 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

A handwritten signature in blue ink, appearing to read "Marc Smith".

Marc Smith
Technical Services Manager



Building something great

Unit 4, 3-5 Gibbon Road,
Baulkham Hills NSW 2153 Australia
PO Box 400,
Winston Hills NSW 2153

T +61 (02) 9624 9900
boral.com.au

TEST REPORT – MILLED SLAG

CLIENT: BORAL CEMENT – MALDON CEMENT

FILE NO: 50/24

ADDRESS: Maldon Bridge Road, Maldon, NSW 2571

REQUEST NO: 110528

LAB SAMPLE NO: 298300

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 08/02/2024

SAMPLE IDENTIFICATION: Enviroment ID # MDDNM2400343- w/e 10/02/2024 - Date sampled: 05/02/2024

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.93	14/02/2024
Relative water requirement	AS 3583.6	99%	15/02/2024
Relative strength 7 days (accelerated)	AS 3583.6	117%	22/02/2024
Relative strength 28 days (standard)	AS 3583.6	115%	14/03/2024

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat File, File

Note:

- Sample supplied by the client and tested as received.

Approved signatory  Sam El-Hamawi
Date 18/03/2024 Serial no. CEM110528.SE.1





**Building
something
great**

TEST REPORT

CLIENT: BORAL CEMENT – MALDON CEMENT
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50 / 24

PROJECT: Testing of Maldon Enviroment Sample.

REQUEST No.: 110528

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 298300
Date Sampled: 05/02/2024
Date Received: 08/02/2024
Date Tested: 18/03/2024
Sample Description: Enviroment
ID # MDDNM2400343
Field No.: 1

TEST RESULTS:

Sulfide Sulfur as S (%) 0.21

Sample submitted by the Client.

- Sample was provided by the Client.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S
19th March 2024.

Parisa Sowti, Violeta Paicu, Brad Vanderburg, Mat.File, File.