## **FINAL REPORT**

CERTIFICATE No.: -



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Environment

PRODUCED AT: Boral Cement Limited Maldon

**TESTED AT:** Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDNM2502875
DATE DESPATCHED: 11/08/2025

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
Insoluble Residue (AS 3583.14)		0.5 %
LOI (AS 3583.3)		-1.2 %
SO <sub>3</sub> (AS 2350.2; TM 10.01.07)		1.5 %
MgO (AS 2350.2)	≤ 15.0 %	6.1 %
Al <sub>2</sub> O <sub>3</sub> (AS 2350.2)	≤ 18.0 %	13.0 %
Fe <sub>2</sub> O <sub>3</sub> (AS 2350.2) expressed as FeO *		1.0 % 0.9 %
$Mn_2O_3$ (AS 2350.2) expressed as MnO *		0.4 % 0.4 %
Total Alkali (AS 2350.2)		0.5 %
CI (AS 2350.2)	≤ 0.1 %	<0.01 %
Fineness passing 45μm sieve (AS 3583.1)		98 %
Fineness Index (AS/NZS 2350.8)		400 m <sup>2</sup> /kg

## **REMARKS**

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

NATA

Melody Mancenido Technical Services Manager

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 11/09/2025

<sup>\*</sup> NATA accreditation does not cover the performance of this service.



## Page 1 of 1 Report Template - Rev. (3) Jul 2021 Authorised by M. A.

#### **Boral Construction Materials**

Materials Technical Services

Unit 4, 3-5 Gibbon Road, Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

> T +61 (02) 9624 9900 boral.com.au

# TEST REPORT - MILLED SLAG

CLIENT:

**BORAL CEMENT - MALDON CEMENT** 

**FILE NO: 50/25** 

ADDRESS:

Maldon Bridge Road, Maldon, NSW 2571

**REQUEST NO: 120110** 

**LAB SAMPLE NO: 326484** 

**SOURCE OF SAMPLE: Maldon** 

**DATE RECEIVED: 14/08/2025** 

SAMPLE IDENTIFICATION: Environment ID # MDDNM2502875 - w/e 16/08/2025 - Date sampled: 11/08/2025

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

**TEST METHOD: AS 3583:** Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density Relative water requirement Relative strength 7 days (accelerated) Relative strength 28 days (standard)	AS 3583.5	2.93	18/08/2025
	AS 3583.6	100%	21/08/2025
	AS 3583.6	116%	28/08/2025
	AS 3583.6	113%	18/09/2025

### Note:

Sample supplied by the client and tested as received.

Approved signator

Serial no.

CEM120110.SE.1

Sam El-Hamawi



