

FINAL REPORT

CERTIFICATE No.: 27766



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Enviroment
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: MDDNM2504511
DATE DESPATCHED: 1/12/2025

PROPERTY	REQUIREMENTS OF AS 3582.2	RESULT
LOI (AS 3583.3)		-0.8 %
MgO (AS 2350.2)	≤ 15.0 %	6.0 %
Al ₂ O ₃ (AS 2350.2)	≤ 18.0 %	13.1 %
Fe ₂ O ₃ (AS 2350.2) expressed as FeO *		0.6 % 0.6 %
Mn ₂ O ₃ (AS 2350.2) expressed as MnO *		0.4 % 0.3 %
Total Alkali (AS 2350.2)		0.5 %
Cl (AS 2350.2)	≤ 0.1 %	< 0.01 %
Fineness passing 45µm sieve (AS 3583.1)		97 %
Fineness Index (AS/NZS 2350.8)		380 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

Melody Mancenido
Technical Services Manager



**Building
something
great**

TEST REPORT

CLIENT: Boral Cement Maldon
Maldon Bridge Road, Maldon, NSW 2571.

FILE No:50/25

PROJECT: Testing of Enviroment Sample from Maldon.

REQUEST No: 121939

TEST PROCEDURE: AS 3583.14 - 1991 – Determination of Insoluble Residue.
AS 3583.8 – Determination of Sulfuric Anhydride content

Laboratory Sample No.: 331910
Date Sampled: 01/12/2025
Date Received: 04/12/2025
Date Tested : 11/12/2025
Sample Description: Enviroment ID #
MDDNM2504511

Field No.: 1

TEST RESULTS:

Insoluble Residue (%) 0.8
Sulphate as SO₃ (m/m %) 1.3

Note:

- Sample was provided by the Client and tested as received.

Approved signatory

Nanthini Selvadurai

Date

12-02-2026

Serial no.

CHEM121939.NS.1





Building
something
great

Unit 4, 3-5 Gibbon Road,
Baulkham Hills NSW 2153 Australia
PO Box 400,
Winston Hills NSW 2153

T +61 (02) 9624 9900
boral.com.au

TEST REPORT

CLIENT: BORAL CEMENT – MALDON CEMENT
Maldon Bridge Road, Maldon, NSW 2571.

FILE No.:50 / 25

PROJECT: Testing of Maldon Environment Weekly Sample.

REQUEST No.: 121939

TEST PROCEDURE: AS 3583.7 – Determination of Sulfide Sulfur content

Laboratory Sample No.: 331910
Date Sampled: 01/12/2025
Date Received: 04/02/2025
Date Tested: 02/02/2026
Sample Description: Environment ID #
MDDNM2504511
Field No.: 1

TEST RESULTS:

Sulfide Sulfur as S (%) 0.17

- Sample was provided by the Client and tested as received.
- Test results in this test report relate only to the sample tested.
- This report shall not be reproduced except in full without the approval of the Boral MTS Laboratory.

Nanthini S
12/02/2026



Building something great

Boral Construction Materials
Materials Technical Services

Unit 4, 3-5 Gibbon Road,
Baulkham Hills NSW 2153 Australia
PO Box 400,
Winston Hills NSW 2153

T +61 (02) 9624 9900
boral.com.au

TEST REPORT – MILLED SLAG

CLIENT: BORAL CEMENT – MALDON CEMENT

FILE NO: 50/25

ADDRESS: Maldon Bridge Road, Maldon, NSW 2571

REQUEST NO: 121939

LAB SAMPLE NO: 331910

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 04/12/2025

SAMPLE IDENTIFICATION: Enviroment ID # MDDNM2504511 - w/e 06/12/2025 - Date sampled: 01/12/2025

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2022

TEST METHOD: AS 3583: Methods of test for supplementary cementitious materials for use with Portland cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Relative density	AS 3583.5	2.94	27/01/2026
Relative water requirement	AS 3583.6	100%	29/01/2026
Relative strength 7 days (accelerated)	AS 3583.6	113%	05/02/2026
Relative strength 28 days (standard)	AS 3583.6	111%	26/02/2026

Note:

- Sample supplied by the client and tested as received.

Approved signatory _____

Date _____

02/03/2026

Sam El-Hamawi

CEM121939.SE.1

Serial no. _____



Accredited for compliance with ISO/IEC 17025 – Testing
This report shall not be reproduced in full without the approval of the Boral MTS Laboratory.
Test results in this Test Report relate only to the samples tested.

NATA Accredited Laboratory
Number: 547