FINAL REPORT

CERTIFICATE No.: 28653

Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Off White Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: MDDOW2603597
DATE DESPATCHED: 1/09/2026

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS/NZS 2350.11)			
3 Day			43.2 MPa
7 Day	Minimum	35 MPa	54.1 MPa
28 Day	Minimum	45 MPa	67.5 MPa
Setting Time (AS/NZS 2350.4)			
Initial	Minimum	45 mins	135 mins
Final	Maximum	360 mins	165 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm	0 mm
SO_3 (AS 2350.2)	Maximum	3.5 %	2.8 %
Cl (AS 2350.2)	Maximum	0.10 %	< 0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL			PHYSICAL		
K_2O	(AS 2350.2)	0.37 %	Normal Consistency	(AS/NZS 2350.3)	28.0 %
Na_2O	(AS 2350.2)	0.08 %	Fineness Index	(AS/NZS 2350.8)	390 m^2/kg
LOI	(AS 2350.2)	4.3 %	Brightness *	(TM 10.01.12)	73.0 %

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.
This cement is a Type GP cement with up to 7.5% mineral addition.
* NATA accreditation does not cover the performance of this service.

Jimmy Zhang
Senior Laboratory Technician

Taleb Hallal
Chemical Analyst

Accredited for compliance with ISO/IEC 17025 - Testing