

FINAL REPORT

CERTIFICATE No.: 27786



Boral Cement Limited
ABN 62 008 528 523

Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Shrinkage Limited Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Boral Cement QA Laboratory
SAMPLE IDENTIFICATION: MDDSL2504553
DATE DESPATCHED: 3/12/2025

PROPERTY	REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (AS/NZS 2350.11)				
3 Day				35.7 MPa
7 Day	Minimum	35 MPa		47.4 MPa
28 Day	Minimum	45 MPa		61.2 MPa
Setting Time (AS/NZS 2350.4)				
Initial	Minimum	45 mins		135 mins
Final	Maximum	600 mins		165 mins
Soundness (AS/NZS 2350.5)	Maximum	5 mm		1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %		2.7 %
Cl (AS 2350.2)	Maximum	0.10 %		0.02 %
Shrinkage (AS 2350.13)				
28 Day Mean	Maximum	750 μ strain		590 μ strain

OTHER REPORTABLE PROPERTIES

CHEMICAL	PHYSICAL		
K ₂ O (AS 2350.2)	0.51 %	Normal Consistency (AS/NZS 2350.3)	27.5 %
Na ₂ O (AS 2350.2)	0.07 %	Fineness Index (AS/NZS 2350.8)	395 m ² /kg
LOI (AS 2350.2)	4.4 %		

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested.

This cement is a Type SL (GP) cement with up to 7.5% limestone mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530

Page 1 of 1



Melody Mancenido
(Technical Services Manager)

Date of Issue: 1/15/2026