



Geo-Fix Paving Joint Mortar

Non-Shrink Mortar

Ready to use, air-cured joint mortar for natural stone, precast concrete paving, stone sets and cobbles. Compacts fast and prevents weed growth. Aids drainage and Covers 9.5 sq mts.

Preparation

Ensure that the paving to be jointed is completely **dry** and free from loose dirt, debris, oil, grease. Where a 'wet' fixing technique has been used to bed the paving, the mortar must be dry before application of the BORAL Paving Joint Mortar. N.B. If rain has occurred prior to application, joints should be allowed to dry before installation of the BORAL Paving Joint Mortar. **It is essential that joint widths have a minimum width of 5mm and a minimum depth of 25mm.**

A trial area should always be undertaken.

Mixing

BORAL Paving Joint Mortar is supplied ready to use and does not require any further mixing or dilution. If foil bag is soft to touch, the vacuum has been broken and the material should not be used. Bags should be hard, but the material inside should be soft and lump free.

Ready to use Paving Joint Mortar



Geo-Fix Paving Joint Mortar

Curing

2-12 hours depending on temperature. Storage Store in a cool dry place. Protect the pack, both outer and inner, from punctures or piercing. Exposure to air will start the curing process.

Shelf life

Minimum of 24 months when stored in unopened vacuum sealed packaging in accordance with the manufacturer's instructions.

Application

Boral Paving Joint Mortar should be used within 45 minutes of opening. In temperatures exceeding 20°C the material should be used within 30 minutes of opening the vacuum sealed bag. Do not use at temperatures below 0°C or in wet weather. Joints on the outside edges of driveways should be firmly bonded using a suitable mortar.

Caution

- Boral Paving Joint Mortar should be protected from rainfall until hardening has taken place.
- Protective covers should not be laid directly onto the paving but lifted clear to allow circulation of air across the application.
- Under no circumstances should uncured Boral Paving Joint Mortar be subject to any water contact.
- Whilst Boral Paving Joint Mortar eliminates the staining problems associated with using sand/cement mortars by not sticking to the paver.
- It should be noted that on certain types of paving, differences in porosity, texture and colour may be highlighted by using the jointing compound.
- Boral Paving Joint Mortar is not suitable for joints subjected to continuous water immersion and is not suitable for chamfered joints.

Coverage

Coverage Joint Width	Paving Dimension (with a joint depth of 25mm)		
	250x250mm	450x450mm	600x600mm
5mm	6.50m ²	11.00m ²	13.25m ²
6mm	5.50m ²	9.50m ²	11.00m ²
7mm	4.50m ²	8.25m ²	8.75m ²
8mm	3.90m ²	7.25m ²	8.25m ²
9mm	3.25m ²	6.00m ²	7.25m ²
10mm	2.90m ²	5.50m ²	6.50m ²

Application




Step 1

Carefully open the vacuum-packed bag and sprinkle BORAL Paving Joint Mortar over the area to be jointed.




Step 2

Using a soft brush, push the BORAL Paving Joint Mortar into the joints at a 45° angle.



Step 3

Firmly compact the BORAL Paving Joint Mortar with a Jointing tool. Refill and repeat ensuring a fully compacted and topped joint.



Step 4

Finish the surface decoratively giving a smooth, flat finish with a Jointing tool then move onto the next area. Firm compaction is the key to the successful laying of BORAL Paving Joint Mortar.



Step 5

After application brush off excess with a soft brush, taking care not to brush out any BORAL Paving Joint Mortar from treated joints. Once cured, sit back and enjoy your new patio.