

FINAL REPORT

CERTIFICATE No.: 22081



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222
F +61 2 4860 2257

TEST CERTIFICATE OF: Berrima Daily Despatch Shrinkage Limited Cement
PRODUCED AT: Boral Cement Limited Berrima
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: BDDSL2100100
DATE DESPATCHED: 14/01/2021

| PROPERTY | REQUIREMENTS OF AS 3972 | | RESULT |
|-----------------------------------|-------------------------|------------------|------------------|
| Compressive Strength (AS 2350.11) | | | |
| 3 Day | | | 38.2 MPa |
| 7 Day | Minimum | 35 MPa | 51.8 MPa |
| 28 Day | Minimum | 45 MPa | 64.0 MPa |
| Setting Time (AS 2350.4) | | | |
| Initial | Minimum | 45 mins | 105 mins |
| Final | Maximum | 600 mins | 165 mins |
| Soundness (AS 2350.5) | Maximum | 5 mm | 1 mm |
| SO ₃ (AS 2350.2) | Maximum | 3.5 % | 2.6 % |
| Cl (AS 2350.2) | Maximum | 0.10 % | 0.02 % |
| Shrinkage (AS 2350.13) | | | |
| 28 Day Mean | Maximum | 750 μ strain | 580 μ strain |

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.50 %
Na₂O (AS 2350.2) 0.06 %
LOI (AS 2350.2) 3.6 %

PHYSICAL

Normal Consistency (AS 2350.3) 28.7 %
Fineness Index (AS 2350.8) 405 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type SL (GP) cement with up to 7.5% limestone mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith
Technical Services Manager
Date of Issue: 19/02/2021