FINAL REPORT

CERTIFICATE No.: 23957



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong Daily Despatch General Purpose Bulk Cement

PRODUCED AT: Boral Cement Limited Geelong

TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: GDDGP2202557

DATE DESPATCHED: 31/07/2022

| PROPERTY | | REQUIREME | REQUIREMENTS OF AS 3972 | | RESULT |
|-------------------------------|-------------|-----------|-------------------------|-------------|-----------|
| Compressive Strength (| AS 2350.11) | | | | |
| 3 Day | , | | | | 36.3 MPa |
| 7 Day | | Minimum | 35 MPa | | 48.7 MPa |
| 28 Day | | Minimum | 45 MPa | | 61.4 MPa |
| Setting Time (AS 2350. | 4) | | | | |
| Initial | | Minimum | 45 mins | | 120 mins |
| Final | | Maximum | 360 mins | | 165 mins |
| Soundness (AS 2350.5 |) | Maximum | 5 mm | | 1 mm |
| SO ₃ (AS 2350.2) | | Maximum | 3.5 % | | 2.8 % |
| CI (AS 2350.2) | | Maximum | 0.10 % | | 0.01 % |
| OTHER REPORTABLE | PROPERTIES | | | | |
| CHEMICAL | | | PHYSICAL | | |
| K ₂ O (AS 2350.2) | 0.41 % | | Normal Consistency | (AS 2350.3) | 27.3 % |
| Na ₂ O (AS 2350.2) | 0.25 % | | Fineness Index | (AS 2350.8) | 405 m²/kg |
| LOI (AS 2350.2) | 2.9 % | | | | |

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Accredited for compliance with ISO/IEC 17025 - Testing

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

Jul.

Marc Smith
Technical Services Manager

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 27/09/2022