FINAL REPORT

CERTIFICATE No.: 24367



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Geelong Daily Despatch General Purpose Bulk Cement
PRODUCED AT:	Boral Cement Limited Geelong
TESTED AT:	Berrima Works Laboratory
SAMPLE IDENTIFICATION:	GDDGP2204427
DATE DESPATCHED:	3/12/2022

PROPERTY	REQUIREM	ENTS OF AS 3972	RESULT			
Compressive Strength (AS 2350.11)						
3 Day			34.6 MPa			
7 Day	Minimum	35 MPa	45.5 MPa			
28 Day	Minimum	45 MPa	60.7 MPa			
Setting Time (AS 2350.4)						
Initial	Minimum	45 mins	135 mins			
Final	Maximum	360 mins	165 mins			
Soundness (AS 2350.5)	Maximum	5 mm	1 mm			
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.8 %			
CI (AS 2350.2)	Maximum	0.10 %	0.02 %			

THER REPORTABLE PROPERTIES			
HEMICAL	PHYSICAL		
₂ O (AS 2350.2) 0.46 %	Normal Consistency	(AS 2350.3)	27.7 %
a ₂ O (AS 2350.2) 0.19 %	Fineness Index	(AS 2350.8)	400 m ² /kg
OI (AS 2350.2) 2.9 %			

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12. Sampling not carried out by laboratory. Samples tested as received. This cement is a Type GP cement with up to 7.5% mineral addition.

Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith Technical Services Manager Date of Issue: 13/01/2023

Page 1 of 1