

# FINAL REPORT

CERTIFICATE No.: 24885



Boral Cement Limited  
N 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222

**TEST CERTIFICATE OF:** Geelong High Early Strength Cement  
**PRODUCED AT:** Boral Cement Limited Geelong  
**TESTED AT:** Berrima Works Laboratory  
**SAMPLE IDENTIFICATION:** GWDHE2301769  
**DATE DESPATCHED:** 15/05/2023

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	39.7 MPa
7 Day	Minimum	40 MPa	51.0 MPa
28 Day			61.3 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	75 mins
Final	Maximum	360 mins	120 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %	2.5 %
Cl (AS 2350.2)	Maximum	0.10 %	0.01 %

## OTHER REPORTABLE PROPERTIES

### CHEMICAL

K<sub>2</sub>O (AS 2350.2) 0.30 %  
Na<sub>2</sub>O (AS 2350.2) 0.22 %  
LOI (AS 2350.2) 1.0 %

### PHYSICAL

Normal Consistency (AS 2350.3) 32.5 %  
Fineness Index (AS 2350.8) 460 m<sup>2</sup>/kg

## REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.  
Sampling not carried out by laboratory. Samples tested as received.  
This cement is a Type HE (GP) cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith  
Technical Services Manager