

FINAL REPORT

CERTIFICATE No.: 25174



Boral Cement Limited

N 62 008 528 523

Taylor Avenue New Berrima NSW 2577

Locked Bag 4 New Berrima NSW 2577

T +61 2 4860 2222

TEST CERTIFICATE OF: Geelong High Early Strength Cement
PRODUCED AT: Boral Cement Limited Geelong
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: GWDHE2303300
DATE DESPATCHED: 16/08/2023

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	44.5 MPa
7 Day	Minimum	40 MPa	54.8 MPa
28 Day			63.9 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	105 mins
Final	Maximum	360 mins	135 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.6 %
Cl (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.31 %
Na₂O (AS 2350.2) 0.15 %
LOI (AS 2350.2) 1.0 %

PHYSICAL

Normal Consistency (AS 2350.3) 32.7 %
Fineness Index (AS 2350.8) 470 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type HE (GP) cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager