

# FINAL REPORT

CERTIFICATE No.: 22495



Boral Cement Limited  
ABN 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222  
F +61 2 4860 2257

**TEST CERTIFICATE OF:** Berrima Weekly Despatch Imported White Cement  
**PRODUCED AT:** Imported Product  
**TESTED AT:** Berrima Works Laboratory  
**SAMPLE IDENTIFICATION:** JKDWC2101520  
**DATE DESPATCHED:** 17/05/2021

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day	Minimum	25 MPa	45.8 MPa
7 Day	Minimum	40 MPa	55.2 MPa
28 Day			64.4 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	90 mins
Final	Maximum	360 mins	150 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO <sub>3</sub> (AS 2350.2)	Maximum	3.5 %	3.2 %
Cl (AS 2350.2)	Maximum	0.10 %	0.05 %

## OTHER REPORTABLE PROPERTIES

### CHEMICAL

K<sub>2</sub>O (AS 2350.2) 0.37 %  
Na<sub>2</sub>O (AS 2350.2) 0.16 %  
LOI (AS 2350.2) 3.3 %

### PHYSICAL

Normal Consistency (AS 2350.3) 29.7 %  
Fineness Index (AS 2350.8) 370 m<sup>2</sup>/kg  
Brightness \* (TM 10.01.12) 88.9 %

## REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

\* NATA accreditation does not cover the performance of this service.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith

Technical Services Manager  
Date of Issue: 9/07/2021