

FINAL REPORT

CERTIFICATE No.: 25179



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Marulan Quicklime Fines - Despatch Composite
PRODUCED AT: Boral Cement Limited Marulan
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: LDQLF2303306
DATE SAMPLED: for date ending 9/08/2023

PROPERTY	RESULT
Chemical Composition (AS 4489.5.1)	
CaO	93.3 %
MgO	0.6 %
Al ₂ O ₃	0.4 %
SiO ₂	0.9 %
K ₂ O	0.1 %
Fe ₂ O ₃	0.2 %
LOI (AS 4489.7.1)	4.6 %
ALI as CaO (AS 4489.6.1)	86.6 %
Slaking (AS 4489.3.1)	
Temperature Rise at 30 s	41.0 °C
Temperature Rise at 3 min	50.0 °C
Total Temperature Rise	52.0 °C
Total Active Slaking Time	6.0 mins
Residue on Slaking	0.58 %
Particle Size Distribution * (AS 1141.11.1)	
< 4.75 mm	100 %
< 2.36 mm	100 %
< 1.18 mm	99 %
< 600 µm	93 %

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

* Samples are not washed.



Accredited for compliance with ISO/IEC 17025 - Testing

A handwritten signature in blue ink, appearing to read "Marc Smith".

Marc Smith
Technical Services Manager