## **FINAL REPORT**

CERTIFICATE No.: 22679



Boral Cement Limited ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577

> T +61 2 4860 2222 F +61 2 4860 2257

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bagged Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MBGGP2102135
DATE DESPATCHED: 13/07/2021

PROPERTY		REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (A	AS 2350.11)				
3 Day	,				32.1 MPa
7 Day		Minimum	35 MPa		44.6 MPa
28 Day		Minimum	45 MPa		61.7 MPa
Setting Time (AS 2350.	4)				
Initial		Minimum	45 mins		120 mins
Final		Maximum	360 mins		165 mins
Soundness (AS 2350.5)		Maximum	5 mm		1 mm
SO <sub>3</sub> (AS 2350.2)		Maximum	3.5 %		2.9 %
CI (AS 2350.2)		Maximum	0.10 %		0.02 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K <sub>2</sub> O (AS 2350.2)	0.39 %		Normal Consistency	(AS 2350.3)	26.8 %
Na <sub>2</sub> O (AS 2350.2)	0.19 %		Fineness Index	(AS 2350.8)	$380 \text{ m}^2/\text{kg}$
LOI (AS 2350.2)	3.1 %				·

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

Jul.

Marc Smith
Technical Services Manager
Date of Issue: 2/09/2021

NATA Accreditation Number: 530 / 531 Page 1 of 1

Accredited for compliance with ISO/IEC 17025 - Testing