FINAL REPORT

CERTIFICATE No.: 23993



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Maldon Daily Despatch General Purpose Bagged Cement
PRODUCED AT:	Boral Cement Limited Maldon
TESTED AT:	Berrima Works Laboratory
SAMPLE IDENTIFICATION:	MBGGP2202626
DATE DESPATCHED:	5/08/2022

PROPERTY	REQUIREM	ENTS OF AS 3972	RESULT
Compressive Strength (AS 2350.11)			
3 Day			31.6 MPa
7 Day	Minimum	35 MPa	46.4 MPa
28 Day	Minimum	45 MPa	62.7 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	150 mins
Final	Maximum	360 mins	180 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.7 %
CI (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE CHEMICAL		PHYSICAL		
K ₂ O (AS 2350.2)	0.52 %	Normal Consistency	(AS 2350.3)	26.8 %
Na ₂ O (AS 2350.2)	0.09 %	Fineness Index	(AS 2350.8)	365 m²/kg
LOI (AS 2350.2)	2.1 %			C C

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12. Sampling not carried out by laboratory. Samples tested as received. This cement is a Type GP cement with up to 7.5% mineral addition.

Marc Smith Technical Services Manager Date of Issue: 27/09/2022

Accredited for compliance with ISO/IEC 17025 - Testing