FINAL REPORT

CERTIFICATE No.: 24517



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Maldon Daily Despatch General Purpose Bagged Cement
PRODUCED AT:	Boral Cement Limited Maldon
TESTED AT:	Berrima Works Laboratory
SAMPLE IDENTIFICATION:	MBGGP2300335
DATE DESPATCHED:	7/02/2023

PROPERTY	REQUIREM	REQUIREMENTS OF AS 3972				
Compressive Strength (AS 2350.11)						
3 Day			32.6 MPa			
7 Day	Minimum	35 MPa	46.1 MPa			
28 Day	Minimum	45 MPa	60.0 MPa			
Setting Time (AS 2350.4)						
Initial	Minimum	45 mins	165 mins			
Final	Maximum	360 mins	210 mins			
Soundness (AS 2350.5)	Maximum	5 mm	0 mm			
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.5 %			
CI (AS 2350.2)	Maximum	0.10 %	0.02 %			

CHEMICAL K ₂ O (AS 2350.2) 0.53 %	PHYSICAL Normal Consistency	(10 2250 2)	
1.20 (7.0 2000.2) 0.00 70	Normal Consistency	(AS 2350.3)	25.5 %
Na ₂ O (AS 2350.2) 0.09 %	Fineness Index	(AS 2350.8)	405 m ² /kg
LOI (AS 2350.2) 2.7 %			

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12. Sampling not carried out by laboratory. Samples tested as received. This cement is a Type GP cement with up to 7.5% mineral addition.

Marc Smith Technical Services Manager Date of Issue: 23/03/2023

Accredited for compliance with ISO/IEC 17025 - Testing