FINAL REPORT

CERTIFICATE No.: 24922



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bagged Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MBGGP2301945

DATE DESPATCHED: 1/06/2023

PROPERTY		REQUIREMI	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)				
3 Day					32.7 MPa
7 Day		Minimum	35 MPa		47.3 MPa
28 Day		Minimum	45 MPa		60.2 MPa
Setting Time (AS 2350.	4)				
Initial		Minimum	45 mins		180 mins
Final		Maximum	360 mins		255 mins
Soundness (AS 2350.5)		Maximum	5 mm		0 mm
SO ₃ (AS 2350.2)		Maximum	3.5 %		2.6 %
CI (AS 2350.2)		Maximum	0.10 %		0.02 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K ₂ O (AS 2350.2)	0.60 %		Normal Consistency	(AS 2350.3)	27.0 %
Na ₂ O (AS 2350.2)	0.10 %		Fineness Index	(AS 2350.8)	$375 \text{ m}^2/\text{kg}$
LOI (AS 2350.2)	2.9 %			•	`

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Accredited for compliance with ISO/IEC 17025 - Testing

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

JW.

Marc Smith
Technical Services Manager
Pate of Issue: 28/07/2023

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 28/07/2023