## **FINAL REPORT**

CERTIFICATE No.: 25612



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bagged Cement

PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MBGGP2304789
DATE DESPATCHED: 13/11/2023

PROPERTY		REQUIREMENTS OF AS 3972			RESULT
Compressive Strength (A	AS 2350.11)				
3 Day	,				33.7 MPa
7 Day		Minimum	35 MPa		46.7 MPa
28 Day		Minimum	45 MPa		61.8 MPa
Setting Time (AS 2350.	4)				
Initial		Minimum	45 mins		150 mins
Final		Maximum	360 mins		210 mins
Soundness (AS 2350.5)	)	Maximum	5 mm		0 mm
SO <sub>3</sub> (AS 2350.2)		Maximum	3.5 %		2.5 %
CI (AS 2350.2)		Maximum	0.10 %		0.02 %
OTHER REPORTABLE	PROPERTIES				
CHEMICAL			PHYSICAL		
K <sub>2</sub> O (AS 2350.2)	0.56 %		Normal Consistency	(AS 2350.3)	27.7 %
Na <sub>2</sub> O (AS 2350.2)	0.07 %		Fineness Index	(AS 2350.8)	355 m <sup>2</sup> /kg
LOI (AS 2350.2)	3.0 %			•	•

## **REMARKS**

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Accredited for compliance with ISO/IEC 17025 - Testing

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GP cement with up to 7.5% mineral addition.

JW.

Marc Smith
Technical Services Manager
Pote of January 12/01/2024

NATA Accreditation Number: 530 / 531 Page 1 of 1 Date of Issue: 12/01/2024