

FINAL REPORT

CERTIFICATE No.: 23019



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222
F +61 2 4860 2257

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDBU2103450
DATE DESPATCHED: 10/11/2021

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
SO ₃ (TM 10.01.07)	Maximum	3.5 %	2.3 %
Cl (AS 2350.2)	Maximum	0.10 %	0.02 %

OTHER REPORTABLE PROPERTIES

CHEMICAL	PHYSICAL		
	Fineness Index	(AS 2350.8)	375 m ² /kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type GB cement with nominally 35% slag.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager

Date of Issue: 29/03/2022

TEST REPORT

CLIENT: BORAL CEMENT – (TECHNICAL)

FILE NO: 50/22

ADDRESS: 39 Delhi Road, North Ryde, NSW 2113

REQUEST NO: 98408

TEST METHOD: AS/NZS 2350: Method of Testing Portland and Blended Cements

CEMENT IDENTIFICATION: MDDBU2103450

LAB. SAMPLE NO: 264213

SAMPLE SOURCE: Maldon

DATE SAMPLED: 10/11/2021

DATE RECEIVED: 04/03/2022

Results


Date of cast: 07/03/2022

PROPERTY	DATE TESTED	TEST METHOD	RESULT
Compressive strength - 3 days	10/03/2022	AS/NZS 2350.11	19.6 MPa
Compressive strength - 7 days	14/03/2022	AS/NZS 2350.11	28.0 MPa
Compressive strength - 28 days	04/04/2022	AS/NZS 2350.11	44.3 MPa
Normal Consistency	01/04/2022	AS/NZS 2350.3	28.5%
Setting Time Initial Set	01/04/2022	AS/NZS 2350.4	180 Minutes
Final Set	01/04/2022	AS/NZS 2350.4	270 Minutes
Soundness	02/04/2022	AS/NZS 2350.5	1 mm

Note:

- Cement was provided by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory  Julius Alvaro
Date 12/04/2022 Serial No. CEM98408.JA.1

