

# FINAL REPORT

CERTIFICATE No.: 23135



Boral Cement Limited  
ABN 62 008 528 523  
Taylor Avenue New Berrima NSW 2577  
Locked Bag 4 New Berrima NSW 2577  
T +61 2 4860 2222  
F +61 2 4860 2257

**TEST CERTIFICATE OF:** Maldon Daily Despatch Builders Cement  
**PRODUCED AT:** Boral Cement Limited Maldon  
**TESTED AT:** Berrima Works Laboratory  
**SAMPLE IDENTIFICATION:** MDDBU2103863  
**DATE DESPATCHED:** 13/12/2021

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
SO <sub>3</sub> (TM 10.01.07)	Maximum	3.5 %	2.2 %
Cl (AS 2350.2)	Maximum	0.10 %	0.02 %

## OTHER REPORTABLE PROPERTIES

CHEMICAL	PHYSICAL		
	Fineness Index	(AS 2350.8)	395 m <sup>2</sup> /kg

## REMARKS

Sampling not carried out by laboratory. Samples tested as received.  
This cement is a Type GB cement with nominally 35% slag.



Accredited for compliance with ISO/IEC 17025 - Testing

A handwritten signature in blue ink, appearing to read "Marc Smith".

Marc Smith  
Technical Services Manager

Date of Issue: 29/03/2022

**TEST REPORT****CLIENT:** BORAL CEMENT – (TECHNICAL)**FILE NO:** 50/22**ADDRESS:** 39 Delhi Road, North Ryde, NSW 2113**REQUEST NO:** 98364**TEST METHOD:** AS/NZS 2350: Method of Testing Portland and Blended Cements**CEMENT IDENTIFICATION:** MDDBU2103863**LAB. SAMPLE NO:** 264105**SAMPLE SOURCE:** Maldon**DATE SAMPLED:** 13/12/2021**DATE RECEIVED:** 01/03/2022**Results**Date of cast: 04/03/2022

PROPERTY	DATE TESTED	TEST METHOD	RESULT
Compressive strength - 3 days	07/03/2022	AS/NZS 2350.11	20.1 MPa
Compressive strength - 7 days	11/03/2022	AS/NZS 2350.11	34.3 MPa
Compressive strength - 28 days	01/04/2022	AS/NZS 2350.11	46.5 MPa
Normal Consistency	28/03/2022	AS/NZS 2350.3	28.7%
Setting Time Initial Set	28/03/2022	AS/NZS 2350.4	195 Minutes
Final Set	28/03/2022	AS/NZS 2350.4	270 Minutes
Soundness	29/03/2022	AS/NZS 2350.5	1 mm

**Note:**

- Cement was provided by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory



Julius Alvaro

Date

04/04/2022

Serial No.

CEM98364.JA.23

