FINAL REPORT

CERTIFICATE No.:   23401

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDBU2200619
DATE DESPATCHED: 10/03/2022

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
SO_3 (TM 10.01.07)	Maximum	3.5 %	2.1 %
Cl (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL   **PHYSICAL**

Fineness Index	(AS 2350.8)	390 m^2/kg

REMARKS

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GB cement with nominally 35% slag.

Marc Smith
Technical Services Manager

Date of Issue: 19/05/2022

BORAL™

Boral Construction Materials
Materials Technical Services

Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia

PO Box 400, Winston Hills NSW 2153

T +61 (02) 9624 9900

boral.com.au

TEST REPORT

CLIENT:	BORAL CEMENT – (TECHNICAL)	**FILE NO:**	50/22
ADDRESS:	39 Delhi Road, North Ryde, NSW 2113	**REQUEST NO:**	98636

TEST METHOD: AS/NZS 2350: Method of Testing Portland and Blended Cements

CEMENT IDENTIFICATION:	MDDBU2200619	**LAB. SAMPLE NO:**	264851
SAMPLE SOURCE:	Maldon	**DATE SAMPLED:**	10/03/2022
DATE RECEIVED:	17/03/2022		

Results

Date of cast: 24/03/2022

PROPERTY	DATE TESTED	TEST METHOD	RESULT
Compressive strength - 3 days	27/03/2022	AS/NZS 2350.11	19.0 MPa
Compressive strength - 7 days	31/03/2022	AS/NZS 2350.11	30.6 MPa
Compressive strength - 28 days	21/04/2022	AS/NZS 2350.11	44.9 MPa
Normal Consistency	12/04/2022	AS/NZS 2350.3	28.5%
Setting Time Initial Set	12/04/2022	AS/NZS 2350.4	165 Minutes
Final Set	12/04/2022	AS/NZS 2350.4	270 Minutes
Soundness	13/04/2022	AS/NZS 2350.5	1 mm

Note:
- Cement was provided by the client and tested as received.

Marc Smith, Parisa Sowti, Violeta Paicu, Mat. File, File

Approved Signatory _Julius C. Alvaro_ Julius Alvaro

Date _07/05/2022_   Serial No. _CEM98636.JA.18_

NATA Accredited Laboratory
Number: 547