FINAL REPORT

CERTIFICATE No.: 24047



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement

PRODUCED AT: Boral Cement Limited Maldon

TESTED AT: Berrima Works Laboratory

SAMPLE IDENTIFICATION: MDDBU2202764

DATE DESPATCHED: 16/08/2022

PROPERTY	REQUIREME	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)				
3 Day				20.5 MPa
7 Day	Minimum	20 MPa		34.1 MPa
28 Day	Minimum	35 MPa		54.1 MPa
Setting Time (AS 2350.4)				
Initial	Minimum	45 mins		210 mins
Final	Maximum	600 mins		255 mins
Soundness (AS 2350.5)	Maximum	5 mm		1 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %		2.3 %
CI (AS 2350.2)	Maximum	0.10 %		0.01 %
OTHER REPORTABLE PROPERTIES				
CHEMICAL		PHYSICAL		
		Normal Consistency	(AS 2350.3)	29.0 %
		Fineness Index	(AS 2350.8)	$370 \text{ m}^2/\text{kg}$

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GB cement with nominally 35% slag.

Jul

Marc Smith
Technical Services Manager

Page 1 of 1 Date of Issue: 17/10/2022

NATA Accreditation Number: 530 / 531