FINAL REPORT

CERTIFICATE No.: 24417



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Maldon Daily Despatch Builders Cement
PRODUCED AT:	Boral Cement Limited Maldon
TESTED AT:	Berrima Works Laboratory
SAMPLE IDENTIFICATION:	MDDBU2204553
DATE DESPATCHED:	19/12/2022

PROPERTY	REQUIREM	ENTS OF AS 3972	RESULT
Compressive Strength (AS 2350.11)			
3 Day			17.6 MPa
7 Day	Minimum	20 MPa	27.7 MPa
28 Day	Minimum	35 MPa	46.4 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	210 mins
Final	Maximum	600 mins	285 mins
Soundness (AS 2350.5)	Maximum	5 mm	1 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %	2.5 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES CHEMICAL

CHEMICAL	PHYSICAL		
	Normal Consistency	(AS 2350.3)	28.7 %
	Fineness Index	(AS 2350.8)	360 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12. Sampling not carried out by laboratory. Samples tested as received. This cement is a Type GB cement with nominally 35% slag.

W

Marc Smith Technical Services Manager Date of Issue: 15/02/2023

Accredited for compliance with ISO/IEC 17025 - Testing