

FINAL REPORT

CERTIFICATE No.: 24714



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDBU2301049
DATE DESPATCHED: 27/03/2023

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			22.4 MPa
7 Day	Minimum	20 MPa	35.4 MPa
28 Day	Minimum	35 MPa	54.4 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	210 mins
Final	Maximum	600 mins	300 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %	2.4 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency (AS 2350.3)	28.5 %
Fineness Index (AS 2350.8)	400 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type GB cement with nominally 35% slag.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith
Technical Services Manager
Date of Issue: 5/05/2023