FINAL REPORT

CERTIFICATE No.: 25385



Boral Cement Limited N 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch Builders Cement

> **Boral Cement Limited Maldon** PRODUCED AT: Berrima Works Laboratory

TESTED AT:

SAMPLE IDENTIFICATION: MDDBU2304284 **DATE DESPATCHED:** 16/10/2023

PROPERTY	REQUIREME	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)				
3 Day				19.8 MPa
7 Day	Minimum	20 MPa		29.9 MPa
28 Day	Minimum	35 MPa		48.1 MPa
Setting Time (AS 2350.4)				
Initial	Minimum	45 mins		195 mins
Final	Maximum	600 mins		300 mins
Soundness (AS 2350.5)	Maximum	5 mm		1 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %		2.7 %
CI (AS 2350.2)	Maximum	0.10 %		< 0.01 %
OTHER REPORTABLE PROPERTIES				
CHEMICAL		PHYSICAL		
		Normal Consistency	(AS 2350.3)	28.5 %
		Fineness Index	(AS 2350.8)	360 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received.

This cement is a Type GB cement with nominally 35% slag.

Marc Smith **Technical Services Manager** Date of Issue: 12/12/2023

Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1