

FINAL REPORT

CERTIFICATE No.: 23383



Boral Cement Limited
N 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222

TEST CERTIFICATE OF: Maldon Daily Despatch General Purpose Bulk Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDGP2200571
DATE DESPATCHED: 7/03/2022

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			34.9 MPa
7 Day	Minimum	35 MPa	46.8 MPa
28 Day	Minimum	45 MPa	60.1 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	120 mins
Final	Maximum	360 mins	165 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (AS 2350.2)	Maximum	3.5 %	2.5 %
Cl (AS 2350.2)	Maximum	0.10 %	0.01 %

OTHER REPORTABLE PROPERTIES

CHEMICAL

K₂O (AS 2350.2) 0.38 %
Na₂O (AS 2350.2) 0.19 %
LOI (AS 2350.2) 3.7 %

PHYSICAL

Normal Consistency (AS 2350.3) 28.0 %
Fineness Index (AS 2350.8) 440 m²/kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type GP cement with up to 7.5% mineral addition.



Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith
Technical Services Manager