

FINAL REPORT

CERTIFICATE No.: 22179



Boral Cement Limited
ABN 62 008 528 523
Taylor Avenue New Berrima NSW 2577
Locked Bag 4 New Berrima NSW 2577
T +61 2 4860 2222
F +61 2 4860 2257

TEST CERTIFICATE OF: Maldon Daily Despatch Marine Cement
PRODUCED AT: Boral Cement Limited Maldon
TESTED AT: Berrima Works Laboratory
SAMPLE IDENTIFICATION: MDDMC2100436
DATE DESPATCHED: 16/02/2021

PROPERTY	REQUIREMENTS OF AS 3972		RESULT
Compressive Strength (AS 2350.11)			
3 Day			13.0 MPa
7 Day	Minimum	20 MPa	24.2 MPa
28 Day	Minimum	35 MPa	46.9 MPa
Setting Time (AS 2350.4)			
Initial	Minimum	45 mins	195 mins
Final	Maximum	600 mins	315 mins
Soundness (AS 2350.5)	Maximum	5 mm	0 mm
SO ₃ (TM 10.01.07)	Maximum	3.5 %	1.3 %
CI (AS 2350.2)	Maximum	0.10 %	0.01 %
Peak Temperature (TM 10.01.06)	Maximum	23 °C	14.6 °C

OTHER REPORTABLE PROPERTIES

CHEMICAL

PHYSICAL

Normal Consistency (AS 2350.3)	32.3 %
Fineness Index (AS 2350.8)	425 m ² /kg

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.
Sampling not carried out by laboratory. Samples tested as received.
This cement is a Type LH/SR (GB) cement with nominally 60% slag.



Accredited for compliance with ISO/IEC 17025 - Testing

NATA Accreditation Number: 530 / 531

Page 1 of 1

Marc Smith
Technical Services Manager
Date of Issue: 14/05/2021