

Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

FILE NO: 50/20

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT - MILLED SLAG

CLIENT: BORAL CEMENT – MALDON CEMENT

Address: MALDON BRIDGE ROAD, MALDON, NSW 2571

REQUEST NO: 92327

LAB SAMPLE NO: 247136

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 19/11/2020

SAMPLE IDENTIFICATION: Environment ID # MDDNM2003448 - w/e 21/11/2020 - Date sampled: 16/11/2020

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2019

TEST METHOD: AS3583: Methods of test for supplementary cementitious materials for use with Portland

Cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Fineness by the 45µm sieve Relative density Relative water requirement Relative strength 7 days (accelerated) Relative strength 28 days (standard)	AS 3583.1	99%	03/12/2020
	AS 3583.5	2.91	25/11/2020
	AS 3583.6	100%	26/11/2020
	AS 3583.6	111%	03/12/2020
	AS 3583.6	105%	24/12/2020

Violeta Paicu, Brad Vanderburg, Parisa Sowti, Mat File, File

Note:

Sample was provided by the client and tested as received.



Approved Signatory Serial No. CEM92327.JA.1

Page 1 of 1

Report Template - Rev. (2) April 2017 - Authorised by M.A.



Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

FILE No.:50/20

REQUEST No.: 92327

TEST REPORT

CLIENT:

BORAL CEMENT - Maldon Cement

Maldon Bridge Road, Maldon, NSW 2571.

PROJECT:

Testing of Maldon Environment Weekly Sample.

TEST PROCEDURE:

AS 3583.12 - 1991 - Determination of Available Alkali

Laboratory Sample No.:

247136

Date Sampled:

16/11/20

Date Received:

19/11/20

Date Tested:

17/12/20

Sample Description:

Environment ID#

MDDNM2003448

Field No.:

1

TEST RESULTS:

Sodium as Na₂O (%)

0.07

Potassium as K₂O (%)

0.08

Available Alkali (%)

0.1

Available Alkali (%) = Na_2O (%) + (0.658 x K_2O %)

Note:

Sample submitted by the Client.

V.Paicu, B.Vanderburg, P.Sowti, Mat.File, File.

NATA

ACCREDITED FOR
TECHNICAL

Approved Signatory_

Date 18-12-20

Serial No.

CHEM92327.NS.1

Nanthini Selvadurai