

Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

FILE NO: 50/21

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

TEST REPORT - MILLED SLAG

CLIENT: BORAL CEMENT - MALDON CEMENT

Address: MALDON BRIDGE ROAD, MALDON, NSW 2571

REQUEST NO: 92857 **LAB SAMPLE NO:** 248669

SOURCE OF SAMPLE: Maldon

DATE RECEIVED: 14/01/2021

SAMPLE IDENTIFICATION: Environment ID # MDDNM2003911 - w/e 26/12/2020 - Date sampled: 21/12/2020

IDENTIFICATION OF CEMENT USED: Boral Cement SL Berrima Ref. 2019

TEST METHOD: AS3583: Methods of test for supplementary cementitious materials for use with Portland Cement

PROPERTY	TEST METHOD	RESULT	DATE TESTED
Fineness by the 45µm sieve Relative density Relative water requirement Relative strength 7 days (accelerated) Relative strength 28 days (standard)	AS 3583.1	99%	28/01/2021
	AS 3583.5	2.91	20/01/2021
	AS 3583.6	100%	21/01/2021
	AS 3583.6	102%	28/01/2021
	AS 3583.6	95%	18/02/2021

Violeta Paicu, Brad Vanderburg, Parisa Sowti, Mat File, File

Note:

Sample was provided by the client and tested as received.

NATA

ACCREDITED FOR
TECHNICAL
COMPETENCE

Approved Signatory

Sharjeel Mahmood

Date 19-02-2021

_ Serial No. _

CEM92857.SM.1

Page 1 of 1

Report Template - Rev. (2) April 2017 - Authorised by M.A.



Boral Construction Materials Materials Technical Services

Unit 4, 3-5 Gibbon Road Baulkham Hills NSW 2153 Australia PO Box 400, Winston Hills NSW 2153

T: +61 (02) 9624 9900 F: +61 (02) 9624 9999

www.boral.com.au

FILE No.:50/21

REQUEST No.: 92857

TEST REPORT

CLIENT:

BORAL CEMENT - Maldon Cement

Maldon Bridge Road, Maldon, NSW 2571.

PROJECT:

Testing of Maldon Environment Weekly Sample.

TEST PROCEDURE:

AS 3583.12 – 1991 – Determination of Available Alkali

Laboratory Sample No.: 248669

Date Sampled: 21/12/20

Date Received: 14/01/21

Date Tested: 17/02/21

Sample Description: Environment ID#

MDDNM2003911

1

Field No .:

TEST RESULTS:

Sodium as Na₂O (%) 0.05 Potassium as K₂O (%) 0.05 Available Alkali (%) 0.1

Available Alkali (%) = Na_2O (%) + (0.658 x K_2O %)

Note:

Sample was provided by the Client and tested as received.

V.Paicu, B.Vanderburg, P.Sowti, Mat.File, File.

TECHNICAL

Approved Signatory

Nanthini Selvadurai

18 Date

Accredited for compliance with ISO/IEC 17025 - Testing

CHEM92857.NS.1